

MYCALEX INSULATORS



CRYSTEX COMPOSITES LLC
 Mykroy/Mycalex® Ceramics
 125 Clifton Boulevard, Clifton NJ. 07011
 Phone: +1-973-779-8866 Fax: +1-973-779-2013
www.mycalexinsulators.com



MM60-75

MYCALEX® stand-off insulator



MM60-75

Manufacturing process : TRANSFER MOLDING

MATERIAL: Glass-Mica Ceramic Grade MM451

Operating Temperature -50 to 450°C

ROHS compliant (Pb Free)



Mycalex Insulators are made from inorganic materials that do not burn , glass, mica and metal inserts. Compliant to EN45545-2, NF F16-101 and NF F16-102

CTI - >600

Insert : Nickel Plated Carbon Steel. Brass or Stainless Steel available on request.



Part	Thread Pitch (mm)	Thread Dia. (inch)	Pitch mm	Weight (kg)
MM60-75-M10	2F	M 10	1.50	0.3
MM60-75-M12	2F	M 12	1.75	0.3
MM60-75-M10 /M14	1F	M 14	2.00	0.3
	1F	M 10	1.50	
MM60-75-M14	2F	M 14	2.00	0.3
MM60-75-M16	2F	M 14	2.00	0.3



Dimensional Values	
Height	60mm ± 0.25
Diameter	60mm
Hexagonal across the flats	55mm
Creepage distance	75 mm
Mechanical Characteristics	
Tensile Strength	≥1800 daN
End flexural strength	>650 daN
Compressive strength	≥7000 daN
Torsion 10/14/16	>60/110/140 Nm
Electrical Characteristics	
Arc over voltage in air	>30kV
Breakdown voltage (dry)	>35 kV
Insulation resistance G-Ohm at 1,000V DC	≥200 GΩ
Capacitance (1KHz)	7.5 pF
Test Conditions	
Voltage for 1 minute	27 kV
Frequency	60Hz
Duration	1 min.



Made with pride in the USA

To the best of our knowledge the information contained herein is accurate; however, Crystex Composites LLC does not accept any liability regarding the accuracy or completeness of such information. Purchaser has the sole responsibility in determining the suitability of any material described herein for the use contemplated and the processing of such material by purchaser

MYCALEX INSULATORS